

## SPECIFICATION FOR APPROVAL

### 1. Material

Production:	High Flux Cores
KDM.P/N:	KH401-060A
AL:	92(nH/N <sup>2</sup> ) ± 8%
Material:	60 μ
Coating Color:	Khaki
Coating material:	epoxy
Coating Breakdown Voltage:	1500V, 0.5mA, 2Sec




### 2. Physical Characteristics

Before Coating			After Coating			Le(cm)	Ae(cm <sup>2</sup> )	V(cm <sup>3</sup> )	W(cm <sup>2</sup> )	Weight (g) (ref.)	Box Quantity (Pieces)
OD(Max.) in/mm	ID(Min.) in/mm	Ht(Max.) in/mm	OD(Max.) mm	ID(Min.) mm	Ht(Max.) mm						
4.000 101.60	2.250 57.15	0.535 13.59	103.12	55.75	14.86	24.271	2.972	72.122	24.398	575.1	35


### 3. Electrical Parameters(Typical) Temperature(25°C ± 2°C)

Test Item	Test Condition	Value(Typical)	Test Instrument
Inductance	φ 0.8mm/129Ts, 20kHz/1V, I=0A (Evenly full windings)(均匀绕满)	1531 μ H ± 8%	CH3302
DC-Bias	φ 0.8mm/129Ts, 20kHz/1V, I=15A(H=1000Oe) (Evenly full windings)(均匀绕满)	1126.8 μ H (Min.)	WK3255B+WK3265B
Core Loss	50kHz/1000Gs	300mW/cm <sup>3</sup> (Max.)	SY-8219
Remarks	Set the internal resistance of LCR meter to 100 Ω.(电感测试仪内阻设置100 Ω)		

#### Core Loss Curves(Typical)



#### DC-Bias Curves(Typical)



KDM确认栏  
KDM  
Signature

**科达磁电  
技术部**

客户确认栏  
Customer  
Signature

请在5个工作日内回签承认书，否则此承认书将作为后续订单的OQC标准。若有疑问，请及时联系我司RD部门。  
Please sign back after approval within 5 working days, otherwise this approval sheet would be taken as OQC standard for subsequent orders. If you have any questions, please contact RD department in time.